

**PAT-NO:** JP02006150606A  
**DOCUMENT-IDENTIFIER:** JP 2006150606 A  
**TITLE:** POLYESTER FILM FOR METAL SHEET LAMINATE, FILM LAMINATED METAL SHEET AND METAL CONTAINER  
**PUBN-DATE:** June 15, 2006

**INVENTOR-INFORMATION:**

NAME	COUNTRY
AOKI, AKIHIRO	N/A
SHIMIZU, HIDENORI	N/A
ODA, NAONOBU	N/A

**ASSIGNEE-INFORMATION:**

NAME	COUNTRY
TOYOBO CO LTD	N/A

**APPL-NO:** JP2004340263  
**APPL-DATE:** November 25, 2004

**INT-CL-  
ISSUED:**

TYPE	IPC DATE IPC-OLD
IPCP	B32B15/09 20060101 B32B015/09
IPFC	B65D8/16 20060101 B65D008/16

**ABSTRACT:**

**PROBLEM TO BE SOLVED:** To provide a good polyester film which ensures required characteristics that are, aroma retention, corrosion resistance and low temperature adhesiveness and not affected by the kind of a beverage to be filled and the kind of a metal sheet when used for the production of a metal container, and a film laminated metal sheet and the metal container.

**SOLUTION:** This laminated polyester film is constituted of two layers of A-layer/B-layer and a resin, which forms the A-layer, comprises polyethylene terephthalate while a resin, which forms the B-layer, comprises a mixed polyester composed of a polyester based on butylene terephthalate and a polyester comprising a composition different from the polyester based on butylene terephthalate. The thickness layer of both layers A and B is A-layer:B-layer=75-95:25-5%, the lamination possible temperature of the B-layer and the metal sheet is 200°C or below and the intrinsic viscosities of both resins forming the A-layer and the B-layer are respectively 0.5-0.7.